


SG-200 Corner Angles

- Corner angles for coil winding
- SG-200 high temperature resin system
- 210° C electrical and mechanical
- 6mm, 8mm and 10mm sizes



	English Units	ASTM or UL Procedure	Typical Values	Metric Units	Typical Values
General Information					
Standard Color			Tan		Tan
Standard Length			9 Ft.		2.74 M
Mechanical Properties					
Tensile Strength	D 638	Psi	70,000	Mpa	483
Tensile Modulus	D 638	Psi x 10 ⁶	3.0	Mpa	20,684
Flexural Strength	D 790	Psi	80,000	Mpa	552
Flexural Modulus	D 790	Psi x 10 ⁶	3.9	Mpa	26,890
Compressive Strength – axial	D 695	Psi	50,000	Mpa	345
Compressive Strength – transverse	D 695	Psi	14,000	Mpa	96
IZOD Impact Strength	D 256	Ft.lb./in.	40	J/cm	21.4
Shear Strength – in plane	D 3914	Psi	3,000	Mpa	20.7
Electrical Properties					
Electrical Strength – 1" axial in oil	D 149	kV/in	70	kV/mm	2.8
Arc Resistance	D 495	seconds	150	seconds	150
Permittivity, 60 Hz	D 150		5.0		5.0
Insulation Resistance	D 257	Ohms x 10 ¹⁴	64	Ohms x 10 ¹⁴	64
Physical Properties					
Water Absorption	D 570	% by wt.	0.15	% by wt.	0.15
Specific Gravity	D 792		1.85		1.85
Flame Resistance	UL 94		HB		HB
Thermal Conductivity	C 177	BTU•In/Hr•Ft ² •°F	2.0	W/mk	0.29
Coefficient of Thermal Expansion	D 696	In/In/°C x 10 ⁻⁵	0.7	mm/mm/°C x 10 ⁻⁵	0.7

Röchling Glastic Composites
 4321 Glenridge Road
 Cleveland, OH 44121 USA
 Tel: 216-486-0100
 Fax: 216-486-1091
www.glastic.com

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

©2007 Röchling Glastic Composites. All Rights Reserved. Printed in USA.

